

Single layer/bilayer transition of electron systems in AlGaAs/GaAs/AlGaAs quantum wells subject to in-plane magnetic fields

L. Smrčka, T. Jungwirth

Institute of Physics, Academy of Science of the Czech Republic,

Cukrovarnická 10, 162 00 Praha 6, Czech Republic

(J. Phys.: Condens. Matter, to be published)

Abstract

Equilibrium properties of electrons in double-heterojunction AlGaAs/GaAs/AlGaAs structures are investigated theoretically, using a full self-consistent numerical method. The transition from single to bilayer electron systems is discussed for the case of double-junction structures with varying distance between interfaces. In strong in-plane magnetic fields we observed the same type of transition accompanied by large effects on the energy spectra. A new phenomenon in bilayer systems — separability of the energy dispersion curve in parts corresponding to electrons either in first or second layer is analyzed in detail. The magnetic field induced variation in the effective distance between electron layers is compared to the constant layers separation in standard double-well structures. Due to relatively small and soft electrostatic barrier between interfaces we expect the van Hove singularity in the 2D density of states to be easier detectable than in double-well systems. The cyclotron mass, proportional to the density of states and characterizing the electron motion in tilted magnetic fields, is calculated as a function of in-plane magnetic field. The separability of the energy spectra resulting in tilted cyclotron

orbits is demonstrated on a classical picture of an electron moving in crossed electric and magnetic fields.

PACS numbers: 72.40, 72.20

I. INTRODUCTION

The electronic structure of bilayer 2D electron systems in double quantum wells is in the focus of interest since their preparation and intensive theoretical and experimental investigation of their properties is now in progress. Main directions of recent research of these structures subjected to magnetic fields were reviewed by Eisenstein [1]. Firstly, in a strong perpendicular magnetic field, the double layer systems exhibit new quantum Hall states not present in a standard 2D gas because of an extra degree of freedom, the layer index. Secondly, in the in-plane magnetic fields, the tunneling between two electron layers can be modified to such extent that, at certain critical fields, the interlayer tunneling is completely suppressed and electrons move exclusively in one of the wells. The field-induced decoupling of electron layers is accompanied by a number of new phenomena which can be studied by measuring both the parallel and perpendicular transport and the Shubnikov-de Haas effect.

A typical double well structure consists of a pair of narrow wells (≈ 20 nm) separated by an undoped AlGaAs barrier of a similar thickness. Two Si doping layers are usually located both below and above the wells and the Schottky gates are deposited on the top/back of the sample to control better the concentration of electrons in individual wells. Due to the tunneling through the barrier the degeneration of the energy spectrum in the layer index is removed, the corresponding single levels split and the lowest bound states of individual wells form a symmetric/antisymmetric pair. A small tunneling probability through the hard-wall AlGaAs barrier implies the small level splitting and the weak coupling of electron layers.

Traditionally, the gross features of the electronic structure of a standard double well are explained in terms of a simple model which assumes two identical very narrow wells at the distance d and a weak overlap of the localized states corresponding to first subbands of both wells. The interwell tunneling is described in the tight binding approximation by a single parameter determining a small bonding-antibonding energy gap. Then the band spectrum is given by the elementary nearly free electron model as presented in classical solid state textbooks (see e.g. [2]). The model predicts the anticrossing of two circular Fermi lines

accompanied by the logarithmic van Hove singularity in the density of states which can be interpreted, in the 2D case, in terms of singular effective cyclotron mass. It was utilized to study a role of minigaps in Si by Ando [3] and Mathesson and Higgins [4] and successfully applied for description of the interwell tunneling (see [1] and references therein) and of the electronic structure of double wells in tilted magnetic fields [5], [6] and [7].

In our theoretical study we shall consider another potentially bilayer systems, the double-heterojunction quantum wells formed only by two selectively doped AlGaAs/GaAs interfaces with no AlGaAs layer grown between them. Note that in this case an undoped structure would result in an exactly rectangular quantum well. In the doped structures, the transfer of electrons from Si donors into the GaAs leads to the band bending in the GaAs by electrostatic forces and, consequently, to the formation of a soft built-in barrier of an approximately parabolic shape inside the well. It depends on the well width and the amount of the charge whether the built-in barrier is strong enough to separate the quantum well into two independent/weakly-coupled parts or if the coupling is so strong that the system can be considered as a transient form between a single well and a double well. For simplicity, only the symmetrically doped wells will be considered.

In charged wells, the shape of the barrier is given by the charge distribution. Therefore the electronic structure must be determined by the self-consistent solution of coupled Schrödinger and Poisson equations. There is a number of such calculations for the case of zero magnetic field, see e.g. [8] and references therein. Effects of the in-plane magnetic field on both conduction and valence bands, resulting in a diamagnetic shift of the electron-hole recombination energy, were discussed by Oliviera *et al.* [9]. Here the full self-consistent calculation will be employed to obtain the electron energy spectra and information about the charge redistribution due to the magnetic field. The electronic structure of double-heterojunction wells will be studied mainly from the point of view of the possible magnetic field induced splitting of a single layer electron system to a bilayer one.

II. BAND STRUCTURE CALCULATION

The standard semi-empirical model working quantitatively for the lowest conduction states of GaAs/AlGaAs heterostructures is used to solve the Schrödinger equation in the envelope function approximation. The envelope function is assumed to be built from host quantum states belonging to a single parabolic band. The effect of the effective mass mismatch is completely neglected and the envelope functions of GaAs and AlGaAs are smoothly matched at the interface. Due to the translational invariance in the layer plane the momentum operators p_x and p_y become good quantum numbers, $p_x \rightarrow \hbar k_x$ and $p_y \rightarrow \hbar k_y$. If we choose a vector potential $\mathbf{A}$ in the form $\mathbf{A} = (B_y z, 0, 0)$, the eigenvalue problem reduces to solving the one-dimensional Schrödinger equation with the Hamiltonian

$$H = \frac{1}{2m} p_z^2 + \frac{m\omega^2}{2} (z - z_0)^2 + V_{conf}(z). \quad (1)$$

For more detailed derivation, consistent with our notation, see e.g. [10] and references therein. The centre z_0 of the the magnetic part of the effective potential energy is related to the wave vector component k_x by $z_0 = \hbar k_x / m\omega$, ω denotes the cyclotron frequency $\omega = |e|B_y/m$. The confining potential energy of a well with the width d

$$V_{conf}(z) = V_b(z) + V_{sc}(z) \quad (2)$$

is a sum of the step functions $V_b(z) = V_b \theta(-z - d/2) + V_b \theta(z - d/2)$ corresponding to the conduction band discontinuities between AlGaAs and GaAs and of a term $V_{sc}(z)$ describing the interaction of an electron with ions and the electron-electron interaction. This term should be calculated self-consistently and can be written as

$$V_{sc}(z) = V_H(z) + V_{xc}(z). \quad (3)$$

The Hartree term V_H is the solution to the Poisson equation

$$\frac{d^2 V_H}{dz^2} = \frac{|e|\varrho(z)}{\epsilon} \quad (4)$$

and we use an expression calculated by Ruden and Döhler [11] in a density-functional formalism for the exchange-correlation term V_{xc} ,

$$V_{xc} \simeq -0.611 \frac{e^2}{4\pi\epsilon} \left(\frac{3N_e(z)}{4\pi} \right)^{1/3}. \quad (5)$$

The conduction band offset V_b and the dielectric constant ϵ enter our calculations as input parameters.

For modulation doped GaAs/AlGaAs heterostructures the total charge density $\varrho(z)$ in the equation (4) can be split into parts corresponding to concentrations of electrons, $N_e(z)$, their parent donors in AlGaAs, $N_d^+(z)$, and ionized residual acceptors in GaAs, $N_a^-(z)$,

$$\varrho(z) = e \left[N_e(z) - N_d^+(z) + N_a^-(z) \right]. \quad (6)$$

We accept a usual approximation of constant impurity concentrations and assume donors and acceptors to be ionized within certain finite intervals: $N_d^+(z) = N_d$ for $d/2 + w \leq |z| \leq d/2 + w + l_d$, i.e. symmetrically with respect to the well of the width d , and $N_a^-(z) = N_a$ for $|z| \leq d/2$, which means that all acceptors inside the well are ionized. Here w denotes the spacer thickness and l_d is the depletion length of donors which is determined in the course of the self-consistent procedure.

III. RESULTS AND DISCUSSION

In our calculation we consider four wells with widths $d = 25, 40, 50$ and 60 nm, close to the dimensions of a typical double quantum well described above. The concentrations of localized charges are $N_d = 2 \times 10^{18} \text{ cm}^{-3}$, $N_a = 10^{14} \text{ cm}^{-3}$, the band offset $V_b = 225 \text{ meV}$ and the dielectric constant $\epsilon = 12.9$. The spacer thickness $w = 60 \text{ nm}$ yields electron systems with the concentration of electrons $N_e \approx 3.2 \times 10^{11} \text{ cm}^{-2}$. The self-consistent procedure was performed in two steps. Firstly, the electronic structure of wells was calculated in zero magnetic field, in the second step the magnetic field dependence of subbands was obtained starting from intermediate zero-field results.

A. Zero magnetic field case

It follows from the form of Hamiltonian (1) that, in the case of zero magnetic field, an electron motion in the z direction is completely decoupled from the in-plane components. The energy spectrum consists of two quasi-continuous free electron branches, the quadratic functions of the wave vector components k_x, k_y , and the energy levels corresponding to the bound states of a well. Positions of levels on energy scale are presented in figure 1, together with the band diagrams resulting from the first step of the self-consistent procedure. The form of the barriers is approximately parabolic for all four wells, the minor deviations from this shape may be observed for wider wells. The heights of barriers are very small when compared with hard walls of wells formed by the GaAs/AlGaAs interfaces. This indicates a stronger coupling between wells than in a standard double-well structure.

All the systems have one occupied pair of symmetric/antisymmetric subbands, except of the 25 nm wide well, where only the subband belonging to the lowest (bonding) state is occupied. Note that the origin of the energy scale in figure 1 is located at the Fermi energy E_F of the electron system. The energy spectrum of the 60 nm system corresponds to almost independent quantum wells, both occupied levels lie below the top of the barrier and the splitting of energy levels due to the quantum tunneling is small. The coupling of 2D electron layers increases smoothly with the decreasing well width and the energy spectrum of the 25 nm well reminds rather of a single well than a double well since the energy difference between the bonding and the antibonding states is comparable with the difference between the energy of the first level and a bottom of the well.

The electron charge density $N_e(z)$ corresponds to well known behaviour of two coupled wells as described by simple tight-binding model: there are two maxima of the density positioned symmetrically in each well, with the small but finite minimum at $z = 0$ for bonding states and $N_e(0) = 0$ for antibonding states. Of course, the maxima are closer and bonding state charge densities higher in narrower double wells.

B. Magnetic field dependent band structure

As seen in figure 1, it is possible to approximate the form of barriers by an expression $-m\Omega^2 z^2/2$, where Ω is the fitting parameter. Assuming further that the barriers are not substantially changed by redistribution of electrons in the magnetic field, the potential energy in (1) is given by a combination of the fixed electric barrier and the attractive magnetic well with the curvature given by B_y . The position of minimum, z_0 , which need not lie inside the interval $-d/2, +d/2$, is determined by k_x . For small magnetic fields the potential energy inside the well is still a barrier with a smaller curvature $m(\omega^2 - \Omega^2)$ and a maximum at $z = z_0 \omega^2/(\omega^2 - \Omega^2)$. At a critical magnetic field, $B_y = m\Omega/|e|$, the bottom of the well becomes a linear function of z , with the slope dependent on k_x , and at higher fields the sign of curvature of the potential energy line is reversed and a minimum appears at z instead of a maximum. The critical fields for the considered wells $B_{60} = 4.7$ T, $B_{50} = 5.6$ T, $B_{40} = 6.7$ T and $B_{25} = 9$ T are fully in the range of experimentally available values. This distinguishes the double-heterojunction structures from the standard double wells with steep AlGaAs barriers in which two deep minima are preserved for arbitrary magnetic fields. Consequently, the simple tight binding picture of eigenfunctions as symmetric/antisymmetric combinations of the eigenstates of individual wells is broken. Above a critical field the lowest eigenstates exhibit always a single maximum and thus electrons are more localized by the magnetic field around its centroid than in the case of standard structures. Examples of eigenfunctions together with ‘electro-magnetic’ potential energy lines defined by equation (1) are presented in figure 2. The results are plotted for selected values of B_y and, to demonstrate their k_x dependence, also for a minimum and a maximum $|k_x|$ corresponding to occupied states.

The transition from a single layer to bilayer electron system, induced by the in-plane magnetic field, is clearly visible in figure 2. Moreover, the effective inter-layer separation increases with the magnetic field reaching a value equivalent to the width of the central GaAs region, in the strong magnetic field limit. These effects are absent in standard double well systems where the distance between 2D electron layers is a constant given by the separation

between wells.

It follows from the above discussion that the in-plane magnetic field does not influence the harmonic dependence of subbands on k_y at all, but the dependence on k_x is changed dramatically. Firstly, the energy separation of bottoms of the bonding/antibonding pair of subbands increases with growing B_y . This process is accompanied by the continuous transfer of electrons from the higher occupied subband to the lower one until the second subband is completely depleted. Secondly, the curvature of the originally parabolic subbands is modified. The antibonding subband remains almost parabolic, similarly as in zero field, only its curvature is slightly higher for larger B_y . The bonding subband exhibits more varied field dependence. The curvature of $E(k_x)$ decreases for k_x around $k_x = 0$, at certain value of k_x reaches zero and then becomes negative. This means that, instead of a minimum which corresponds to a zero field, the local maximum develops at $k_x = 0$, accompanied by two new minima positioned symmetrically around it. For large enough magnetic fields the energy of the maximum becomes greater than the Fermi energy and the spectrum of occupied energies splits into two separated parts. This type of behaviour is general for energy spectra of all four well widths. In the narrowest well the splitting does not occur in the investigated range of fields. Examples of $E(k_x)$ curves for the well of a medium width, $d = 40$ nm, and several selected values of B_y are presented in figure 3.

The electrons with energies close to the Fermi energy E_F are of particular interest since they play essential role in the electronic transport properties of the system. The occupied and empty states are separated by the Fermi lines in $\mathbf{k}$ space. In a zero magnetic field, the Fermi contours corresponding to symmetric and antisymmetric subbands have a form of two concentric circles. The larger circle describes the bonding and the smaller circle the antibonding states. The modification of the shape of $E(k_x)$ curves by the in-plane magnetic fields is reflected also in variation of forms of Fermi contours. They acquire a ‘peanut’ and a ‘lens’ shapes when the sample is subjected to the intermediate magnetic fields. In the strong field limit the ‘lens’ is emptied and the ‘peanut’ is split into two parts belonging to individual wells. This behaviour is illustrated in figure 4 for the same electron system and

the same set of magnetic field values as in figure 3. The deviations from two crossing circles, corresponding to a pair of narrow independent wells, are so large that the shape of Fermi lines can hardly be described by the above mentioned simple model.

C. Cyclotron effective mass and real space trajectories

The separation of electron layers by the in-plane magnetic field may be clearly demonstrated if we consider the electronic structure of a system subjected to a tilted magnetic field with a strong component B_y , parallel to the GaAs/AlGaAs interfaces, and a weak component B_z oriented perpendicularly. To describe the system, the self-consistent quantum mechanical calculation of the electron subbands in the presence of B_y , presented above, is combined with a quasi-classical description of the in plane electron motion under the influence of B_z , as developed originally by Onsager [12] and Lifshitz [13].

The semiclassical theory predicts that an electron is driven by the Lorentz force due to B_z around the Fermi contour with the cyclotron frequency $\omega_c = |e|B_z/m_c$. The cyclotron effective mass m_c , defined by the above equation, is an important characteristics of each Fermi line as a whole and should not be confused with the electron effective mass which is in our case a tensor and an anisotropic function of the position on the Fermi line. The explicit expression relating m_c to the shape of the Fermi contour is

$$m_c = \frac{\hbar^2}{2\pi} \oint \frac{dk}{|\nabla_k E|}, \quad (7)$$

where dk denotes an element of a length of a Fermi line. In the case of two-dimensional electron systems a simple relation holds between the cyclotron effective mass and the density of states g corresponding to a single subband:

$$g = \frac{m_c}{\pi\hbar^2}. \quad (8)$$

Note that this is the cyclotron effective mass, and not the effective mass, which determines e.g. the temperature damping of Shubnikov-de Haas oscillations.

Both equations (7) and (8) can be found, at least in an implicit form, in [12] and [13] already. Since then, they were utilized many times, for application to 2D systems see e.g. [4], but overlooked in the recent publication by Harff *et al.* [14]. Their detailed derivation and discussion for the case of combined parallel and perpendicular magnetic fields is presented in [10].

The magnetic-field dependent cyclotron effective masses resulting from our band structure calculation are shown in figure 5 for all four wells. The logarithmic singularities of the cyclotron mass (density of states) curves corresponding to the lowest subbands occur at higher fields for narrower wells than for broader ones. The position of a singularity is identical with the field value at which a ‘peanut’ becomes a pair of ‘kissing’ Fermi contours, i.e. when it is to split into two independent parts. Note that this is always above the fields $B_{60} = 4.7$ T, $B_{50} = 5.6$ T and $B_{40} = 6.7$ T discussed above. The asymmetric shape of van Hove singularities somewhat deviates from $-\ln|E_F(B_y) - E_0|$ predicted by the analysis based on the quadratic approximation of the energy spectrum near the saddle point. The reason for the slow increase of m_c on the left side from the singularity, and the rapid decrease on the right side, may be due to the large influence of higher order terms in the power expansion of $E(k_x)$. For the Fermi contours of the second subband the cyclotron mass always decreases for the given concentration of electrons.

In the real space, electrons move along trajectories having the shape of Fermi contours but rotated by an angle $\pi/2$ and multiplied by $\hbar/|e|B_z$. A relation exists between the centre of mass $\langle z \rangle$ of an electron state in a well and the energy spectrum $E(k_x)$ modified by the in-plane magnetic field,

$$\langle z \rangle = \frac{\hbar k_x}{m\omega} - \frac{1}{\hbar\omega} \frac{\partial E(k_x)}{\partial k_x}. \quad (9)$$

Since $\langle z \rangle$ is a function of k_x , i.e. of the position of an electron on the Fermi contour, the real space trajectory is slightly tilted with respect to the $x - y$ plane. Travelling around a ‘peanut’ Fermi contour with the frequency ω_c , the electron is transmitted from one well to the other when the wavevector k_x changes its sign. At $k_x = 0$ the electron appears on the

top of the barrier. The separation of a ‘peanut’ into two parts means that two independent real space trajectories for electrons are formed, localized completely in opposite wells. In that case, the electron moving around a Fermi contour is always reflected by the barrier and remains confined in one of the wells. Hence, the electron system can be considered as divided into two disconnected layers. Self-consistently calculated examples of $\langle z \rangle$ as a function of k_x are presented in figure 6.

The quasi-classical model of an electron motion in a double well can help to illustrate the origin of localization of electrons in individual wells due to the magnetic field. Figure 7 shows real space trajectories of an electron in a well with a parabolic barrier calculated classically for the case of two tilted magnetic fields with the same perpendicular component. For the field below the singularity, the trajectory overcomes the barrier and an electron spends the same time in both wells. Note that, in accord with this statement, the left part of the curve (a) lies above and the right part below the projection of the trajectory to the $x - y$ plane, ($z = 0$). The curve (b) is the electron trajectory calculated for the field above the singularity (the curves (a) and (b) are offset for clarity). In that case, an electron is kept all the time in one well. Just at the magnetic field, when the singularity occurs, electron stops at the top of the barrier and stays there infinitely long. It means, in terms utilized above, that its cyclotron frequency is zero and the cyclotron mass goes to infinity.

IV. CONCLUSION

We have performed self-consistent calculations of the electronic structure of symmetrically charged double-heterojunction wells in parallel magnetic fields. Their properties are to the large extent similar to standard double wells but, on the other hand, there are several differences between them which make the double-heterojunctions attractive.

In both types of structures an in-plane magnetic field substantially modifies the k_x dependence of energy subbands. The following properties result from these field induced changes.

(i) Electrons are transferred from the antibonding to the bonding band when magnetic field

increases. (ii) The Fermi contour topology changes, the originally circular lines acquire a ‘peanut’ and a ‘lens’ shapes and, at certain critical fields, the ‘lens’ is emptied (*first critical field*) and the ‘peanut’ splits into two independent lines (*second critical field*). (iii) The splitting of the ‘peanut’ Fermi contour is accompanied by the separation of an electron layer into two independent systems. (iv) At the second critical field the density of electron states and the cyclotron effective mass exhibit a logarithmic singularity when considered as functions of the in-plane field.

The hard wall barrier formed by the AlGaAs layer means that the coupling between electrons in a standard double well is always weak. Therefore, a simple tight binding method for description of an electron motion in the z direction, resulting in a nearly free electron model for its motion in the $x - y$ plane, can be successfully applied to describe the electronic structure.

This is not true for double-heterojunction systems. Due to the charge present inside wells, a soft barrier of approximately parabolic shape is built in each well, with the top in its centre. The height of a barrier is very small and the strength of coupling can be tuned in large range by proper choice of the concentration of carriers and the width of the well. Under these circumstances, the simple model fails to describe the electronic spectra even in a qualitative way. Note, that according to our calculations, e.g. the gap between two occupied subbands increases under the influence of the field, while the simple model yields a constant gap.

The strong coupling between wells means that stronger magnetic fields are necessary to modify the electronic structure of a double-heterojunction. The difference between the first and second critical fields can amount several Tesla and, consequently, also the changes of the cyclotron effective mass are more robust and probably easier to detect experimentally.

Nevertheless, the above described differences between two types of structures are mainly quantitative. The qualitatively new features of double-heterojunction structures are the single layer/bilayer transition and the possible control of the inter-layer separation by in-plane magnetic field. These effects might be useful in studies of many-body effects in bilayer

electron systems.

For these properties the double-heterojunction structures represent a very attractive alternative to standard double wells.

ACKNOWLEDGMENTS

This work has been supported by the Academy of Science of the Czech Republic under Grant No. 110414, by the Grant Agency of the Czech Republic under Grant No. 202/94/1278, by the Ministry of Education, Czech Republic under contract No. V091 and by NSF, U. S., through the grant NSF INT-9106888.

REFERENCES

- [1] J. P. Eisenstein, Superlattices and Microstructures **12**, 107 (1992).
- [2] N. F. Mott and H. Jones, *The Theory of the Properties of Metals and Alloys* (Oxford University Press, London, 1936) p. 59
- [3] T. Ando, J. Phys. Soc. Jpn. **47**, 1595 (1979).
- [4] T. G. Matheson and R. J. Higgins, Phys. Rev. B **25**, 2633 (1982).
- [5] J. Hu. and A. H. MacDonald, Phys. Rev. B **46**, 12 554 (1992).
- [6] S. K. Lyo, Phys. Rev. B **50**, 4965 (1994)
- [7] A. Kurobe, I. M. Gastleton, E. H. Linfield, M. P. Grimshaw, K. M. Brown, D. A. Ritchie, M. Pepper and G. A. C. Jones, Phys. Rev. B **50**, 4889 (1994).
- [8] C. D. Simserides and G. P. Triberis, J. Phys.: Condens. Matter **5**, 6437 (1993).
- [9] G. M. G. Oliviera *et al.*, Phys. Rev. B **35**, 2896 (1987).
- [10] L. Smrčka and T. Jungwirth, J. Phys.: Condens. Matter **6**, 55 (1994).
- [11] P. Ruden and G. H. Döhler, Phys. Rev. B **27**, 3538 (1983).
- [12] L. Onsager, Phil. Mag. **43**, 1006 (1952).
- [13] I. M. Lifshitz, Sov. Phys. - JETP **30**, 63 (1956).
- [14] N. E. Harff, J. A. Simmons, S. K. Lyo, J. F. Klem and S. M. Goodnick, *ICPS-22 Proceedings*, in press

FIGURES

FIG. 1. Band diagrams and energy levels of double-heterojunction wells at a zero magnetic field.

FIG. 2. Wave functions and ‘electro-magnetic’ band diagrams of a double-heterojunction well subject to in-plane magnetic fields. Pairs of curves characterize the electrons with a minimum (dashed) and a maximum (full) occupied $|k_x|$. The width of the well is 40 nm.

FIG. 3. Occupied energy subbands of a double-heterojunction well, $d = 40$ nm, subject to in-plane magnetic fields as functions of k_x .

FIG. 4. Fermi contours of a double-heterojunction well, $d = 40$ nm, subject to in-plane magnetic fields.

FIG. 5. Cyclotron effective masses of four wells as functions of an in-plane magnetic field.

FIG. 6. Centroids of electron states of a double-heterojunction well, $d = 40$ nm, subject to in-plane magnetic fields.

FIG. 7. Classically calculated trajectories of an electron in a double well subject to tilted magnetic field. The upper curve (a) corresponds to B_y below the singularity and the lower curve (b) to B_y above this value.